PCT Applicant's Guide - Volume 14-16aReC'Chaper/PSO ATTORNEY'S DOCKET NUMBER U.S DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE WDUMR-001US ANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) U.S. APPLICATION NO. (If known, see 37 CFR 1.5) CONCERNING A FILING UNDER 35 U.S.C. 371 PRIORITY DATE CLAIMED INTERNATIONAL FILING DATE INTERNATIONAL APPLICATION NO. 09 September 1997 09 September 1998 PCT/AU98/00738 TITLE OF INVENTION CONTAINER WITH INTEGRAL HANDLE, PREFORM AND METHOD OF MANUFACTURE APPLICANT(S) FOR DO/EO/US BEALE, Glenn Robert Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information: This is a FIRST submission of items concerning a filing under 35 U.S.C. 371. This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371. This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1). A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date. A copy of the International Application as filed (35 U.S.C. 371(c)(2)) is transmitted herewith (required only if not transmitted by the International Bureau). has been transmitted by the International Bureau. is not required, as the application was filed in the United States Receiving Office (RO/US). A translation of the International Application into English (35 U.S.C. 371(c)(2)). Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) are transmitted herewith (required only if not transmitted by the International Bureau). have been transmitted by the International Bureau. have not been made; however, the time limit for making such amendments has NOT expired. have not been made and will not be made. A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)). An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)). A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 10. l (35 U.S.C. 371(c)(5)). Items 11. to 16. below concern document(s) or information included: An Information Disclosure Statement under 37 CFR 1.97 and 1.98. An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included. A FIRST preliminary amendment. A SECOND or SUBSEQUENT preliminary amendment. A substitute specification. A change of power of attorney and/or address letter. Other items or information:

IS APPLE THE NO HOT CHIE	500353		L APPLICATION NO 198/00738			ATTORNEY'S DOCKI	
17. X The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)): Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO. \$970.00				CA	LCULATIONS	PTO USE ONLY	
International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$840.00				\$840.00			
International p	oreliminary examinational search fee (37 CFR	n fee (37 CFR 1.445(a)(2)) p	1.482) not paid to US aid to USPTO	SPTO \$760.00			
International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4)				2) \$670.00			
International pand all claims	oreliminary examinations of satisfied provisions of	PCT Article 3	3(1)-(4)	\$96.00			
	ENTER APP	ROPRIATI	E BASIC FEE AN	AOUNT =	\$	970.00	
Surcharge of \$136 months from the	0.00 for furnishing the earliest claimed priority	oath or declar date (37 CFF	ation later than 2 1.492(e)).	0 30	\$	0	
CLAIMS	NUMBER FILED		JMBER EXTRA	RATE			
Total claims	21 -20		1	X \$18.00	\$	18.00	
Independent claims	3 -3		0	X \$78.00	\$	0	
MULTIPLE DEPI	ENDENT CLAIM(S) (if		OVE CALCIII A'	+ \$260.00	\$ \$	988.00	
Reduction of 1/2 for filing by small entity, if applicable. A Small Entity Statement must also by filed (Note 37 CFR 1.9, 1.27, 1.28).					\$	U 0	
			SUBT	TOTAL =	\$	988.00	
Processing fee of \$130.00 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492(f)).				s	0		
TOTAL NATIONAL FEE =				\$	988.00		
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property				\$	0		
TOTAL FEES ENCLOSED =				\$	988.00		
					Ar	nount to be: refunded	\$
						charged	\$
h. Please o	k in the amount of \$charge my Deposit Acc	ount No.				to cov	ver the above fees.
A dupli	cate copy of this sheet	is enclosed.					
c. X The Co overpay	mmissioner is hereby a yment to Deposit Acco	uthorized to c unt No. <u>19</u>	harge any additional 1 <u>-4330</u> . A duplica	fees which may be te copy of this sh	e request is	uired, or credit a s enclosed.	ny
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.							
SEND ALL CORRESPONDENCE TO LOUGH Andrew					1		
STETINA BRUNDA GARRED & BRUCKER 24221 Calle de la Louisa, 4th Floor Laguna Hills, CA 92653 Lo					mynd	ers	
					1 Andrews	_	
				wel	1 Anderson	1	
Pnone: (949) 855-1246			NAME) OC	١٥	
1					99	······································	
				REGISTI	(A 1101	N NUMBER	
1							

<u>0</u>9/508*353* 430 Rec'd PCT/PTO 0 9 маг 2000

"Express Mail" mailing label number <u>EL531408924US</u>
Date of Deposit <u>March 9, 2000</u>

Case No.: WDUMR-001US

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express mail Post Office to Addressee" service under 37 CFR 1 10 on the date indicated above and is addressed to the Commissioner of Patents and Trademarks, Washington, D.C. 20231

SHAUNA S CLARK
(Typed or Printed name of person mailing paper or fee)
(Signature of person mailing paper or fee)

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant:	BEALE, Glenn Robert)	
	,)	Group No.:
Serial No.:	UNKNOWN)	
)	Examiner:
Filed:	HEREWITH)	
)	
For:	CONTAINER WITH)	
INTEGRAL	HANDLE, PREFORM AN	(D)	
METHOD O	F MANUFACTURE)	

PRELIMINARY AMENDMENT

Hon. Commissioner of Patents and Trademarks Box New Application Washington, D.C. 20231

Dear Sir:

Please delete Claims 1-79 and add the following new claims:

- 80. A preform for a container comprised of orientable thermoplastic material and arranged so that the resultant blown container will include a handle or like support structure; said preform comprising a molded structure having a neck portion and an expandable portion below the neck, said neck including a locating ring above the expandable portion and a solid stem or orientable thermoplastics material projecting from the preform and molded integrally therewith which when the container is formed constitutes the handle.
- 81. The preform of Claim 80, wherein the preform is formed by an injection process including two separate, first and second, points of injection.
- 82. The preform of Claim 81, wherein the first point of injection injects non-recycled PET or like thermoplastics material to form a portion of the preform.

- 83. The parison of claim 82, wherein the second point of injection injects PET or like thermoplastics material incorporating at least a portion of recycled material.
- 84. The parison of claim 81, wherein the first point of injection is for the formation of that part of the parison which will be stretched during a stretch blow moulding operation on the parison.
- 85. The parison of claim 84, wherein said second point of injection is for the formation of those parts of said parison which will remain unexpanded or substantially unexpanded in a stretch blow moulding operation on said parison.
- 86. The parison of Claim 80, wherein the preform includes more than one wall profile.
- 87. The parison of Claim 80, wherein the preform has a first wall profile closest to its neck followed by a second wall profile immediately there below and separated therefrom by a first transition zone.
- 88. The parison of Claim 80, wherein the preform has a first wall profile closest to its neck followed by a second wall profile immediately there below and separated therefrom by a first transition zone, and further wherein the preform further includes a third wall profile immediately below said second wall profile and separated therefrom by a second transition zone.
- 89. The parison of Claim 80, further comprising a tag connected to the preform at a location below the handle.
- 90. A method of forming a container having an integral handle; said method comprising:
 - (1) forming a preform having a neck portion and an expandable portion below the neck portion, said neck portion including a locating ring above the expandable portion and a solid stem of orientable thermoplastics material projecting from an external side of the preform and molded integrally with the preform, and
 - (2) performing a blow molding operation on said preform to expand the expandable portion to form the body of the container.

- 91. The method of claim 90, wherein the neck portion and integral handle are subjected to a crystallization step.
- 92. The method of claim 90, wherein the blow molding operation includes supporting the stem whilst the preform is blown in a manner whereby at least a portion of the external side of the body of the container expands to encircle at least a lower portion of the stem so as to form an enclosed grip portion between the external side and the solid stem.
- 93. The method of claim 92, wherein the enclosed grip portion is sized to allow at least two fingers of an adult human hand to pass therethrough.
- 94. The method of claim 90, wherein the stem is formed so as to have an I-shaped cross-section at least throughout that portion of the stem where it projects from the external side of said preform.
 - 95. A container formed by the method of Claim 90
- 96. A parison for an injection stretch blow moulding process, said parison formed by an injection process including two separate, first and second points of injection.
- 97. The parison of claim 96, wherein the first point of injection permits injection of non-recycled PET or like thermoplastics material to form a portion of the parison.
- 98. The parison of claim 96, wherein the second point of injection permits injection of PET or like thermoplastics material incorporating at least a portion of recycled material to form a portion of the parison.
- 99. The parison of claim 96, wherein said first point of injection is for the formation of that part of the parison which will be stretched during a stretch blow moulding operation on the parison.
- 100. The parison of Claim 96, further comprising a tag extending from a lower edge of a handle portion of said preform, the tag being integrally connected to the preform.

REMARKS

This preliminary Amendment is being filed to conform the claims to United States practices.

Respectfully submitted,

Dated: 3/9/00 By:

Lowell Anderson

Registration No. 30,990

STETINA BRUNDA GARRED & BRUCKER

24221 Calle de la Louisa, 4th Floor Laguna Hills, California 92653

(949) 855-1246

LA/ssc

C:\FOREIGN\Wdumr\1usprelm.amd.wpd

FTGRENS (1-9

Peters and Treplance CRic. U.S. DEPARTMENT CREST COMMENT

Peters and Treplance CRic. U.S. DEPARTMENT CREST COMMENT

Links the Parametric Reduction Adjust 1995, he parameters in parameter to department or relevant to the second comment of department comments of department comments of department comments or comments and comments or comments

STATEMENT CLAIMING SMALL ENTITY STATUS (37 CFR 1.9(f) & 1.27(c))—SMALL BUSINESS CONCERN	Doctret Number (Options WDUMR-001US
Gland Dobone BEALE	
Applicant, Patentee, orldentifier. Glenn Robert BEALE Application or Patent No.: 09/508, 353	
Fiedorissued March 69 2000	
	OF MANUFACTURE
I hereby state that I am the owner of the small outliness concern identified below. an official of the small business concern empowered to act on behalf of the concern	
NAME OF SMALL BUSINESS CONCERN BEALETEC PTY LTD	
ADDRESS OF SMALL BUSINESS CONCERN 16-20 Barrack Street. Sunsw 2000, AUSTRALIA	ite 801 Sydney
I hereby state that the above identified small business concern qualifies as a small but 13 CFR Part 121 for purposes of paying reduced fees to the United States Patent and Tradem to size standards for a small business concern may be directed to: Small Business Apminis 409 Tried Steer, SW, Washington, DC 20416.	
I hereby state that rights under contract or law have been conveyed to and remain with identified above with regard to the invention described in,	the small business concern
the specification filed herewith with title as listed above. the application identified above, the patent identified above.	
If the rights held by the above identified small business concern are not exclusive, organization having rights in the invention must file separate statements as to their status as to the invention are held by any person, other than the inventor, who would not qualify as an 37 CFR 1.9(c) if that person made the invention, or by any concern which would not qualify a under 37 CFR 1.9(d), or a nonprofit organization under 37 CFR 1.9(e).	small entities, and no rights
Each person concern, or organization having any rights in the invention is listed below no such person, concern or organization exists.	;
Separate statements are required from each named person, concern or organization histaring their status as small entities. (37 CFR 1.27)	aving rights to the invention
s acknowledge the duty to file, in this application or patent, notification of any change it entitlement to amail antity status prior to paying, or at the time of paying, the earliest of the ist lee due after the date on which status as a small entity is no longer appropriate. (37 CFR 1.2	
NAME OF PERSON SIGNING GLEHM, ROBERT BEA	(v
TITLE OF PERSON IF OTHER THAN OWNER & Director	
LODRESS OF PERSON SIGNING ACOMMINI PL KINGS LAN	61EV
SIGNATURE STEAM DATE	16/10/2000-

Burden Heur Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the fraces of this instribute base. An commente on the emount of time you are required to complete this form should be sent to the Chief information Officer, Patent and Trademark Office Washington, CC 20231. DO NOT SEND FERS OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Apelalant Communitation of Patents



CONTAINER WITH INTEGRAL HANDLE, PREFORM

AND METHOD OF MANUFACTURE

INTRODUCTION

This invention relates to a container with integral handle, preform from which the container is biaxially blown and a method of manufacture thereof.

BACKGROUND OF THE INVENTION

Attempts have been made to incorporate integral handles in PET and like injection blow moulded containers for example see US 4,629,598 to Thompson, assigned to Tri-Tech Systems International, Inc. The parison from which the handled bottles of US 4,629,598 are produced is illustrated in Fig. 1. To date, however, attempts to produce a practical, mass produced version of this arrangement have been unsuccessful. Instead, the best that appears to have been done in commercial practice is an arrangement whereby the blown containers are arranged to accept a clip on or snap on handle in a separate production step after the container itself is formed. See for example WO82/02371 and WO82/02370, both to Thompson.

Injection-stretch-blow moulding is a process in which the parison is stretched both axially and radially, resulting in biaxial orientation.

Biaxial orientation provides increased tensile strength (top load), less permeation due to tighter alignment of the molecules, and improved drop impact, clarity, and lightweighting of the container.

Not all thermoplastics can be oriented. The major thermoplastics used are polyethylene terephthalate (PET), polyacrylonitrile (PAN), polyvinyl chloride (PVC), and polypropylene (PP). PET is by far the largest volume material, followed by PVC, PP, and PAN.

The amorphous materials, e.g., PET, with a wide range of thermoplasticity are easier to stretch-blow than the partially crystalline types such as PP. Approximate melt

5

10

15

20

25

30

35

10

15

20

25

30

35

and stretch temperatures to yield maximum container properties are:

Material	Melt, Degrees C.	Stretch, Degrees C.
PET	280	107
PVC	180	120
PAN	210	120
PP	240	160

There are basically two types of processes for stretch-blow moulding: 1) single-stage in which preforms are made and bottles blown on the same machine, and 2) two-stage in which preforms are made on one machine and blown later on another machine.

Single-stage equipment is capable of processing PVC, PET, and PP. Once the parison is formed (either extruded or injection moulded), it passes through conditioning stations which bring it to the proper orientation temperature. The single-stage system allows the process to proceed from raw material to finished product in one machine, but since tooling cannot be easily changed, the process is best suited for dedicated applications and low volumes.

Oriented PVC containers most commonly are made on single-stage, extrusion-type machines. The parison is extruded on either single- or double-head units. Temperature conditioning, stretching, and thread forming are done in a variety of ways depending on the design of the machine. Many of the processes presently in use are proprietary.

Many oriented PET containers are produced on singlestage machines. Preforms are first injection moulded, then transferred to a temperature conditioning station, then to the blow moulding operation where the preforms are stretchblown into bottles, and finally to an eject station.

With the two-stage process, processing parameters for both preform manufacturing and bottle blowing can be optimized. A processor does not have to make compromises

10

15

20

30

35

for preform design and weight, production rates, and bottle quality as he does on single-stage equipment. either make or buy preforms. And if he chooses to make them, he can do so in one or more locations suitable to his market. Both high-output machines and low output machines are available. Two stage extrusion-type machines generally are used to make oriented PP bottles. In a typical process, preforms are re-extruded, cooled, cut to length, reheated, stretched while the neck finish is being trimmed, and ejected. The two-stage process is the lowest-cost method to produce oriented PET containers. The two-stage process, which permits injection moulding of the preform and then shipping to blow moulding locations, has allowed companies to become preform producers and to sell to blow moulding producers. Thus companies that wish to enter the market with oriented PET containers can minimise their capital requirements. Two-stage stretch-blow moulding also is being used for production of oriented PVC containers. Preform design and its relationship to the final container remains the most critical factor. The proper stretch ratios in the axial and hoop directions must be met if the container is to properly package its intended product.

	Material	Stretch Ratios	Orientation Temp.Deg.F
	PET	16/1	195-240
25	PVC	7/1	210-240
	PAN	9/1	220-260
	PP	6/1	260-280

It is an object of the present invention to produce a practical, readily implementable injection, stretch blow moulded container made from an orientable thermoplastics material incorporating a handle which is formed during and as part of the said injection, stretch blow moulding operation.

SUMMARY OF THE INVENTION

According to one aspect of the invention, there is provided a preform for a container comprised of orientable

10

15

20

25

30

35

thermoplastic material and arranged so that the resultant blown container will include a handle or like support structure; said preform comprising a moulded structure having a neck portion and an expandable portion below the neck, said neck including a locating ring above the expandable portion and a solid stem of orientable thermoplastics material projecting from the preform and moulded integrally therewith which when the container is formed constitutes the handle.

Preferably said stem projects from said locating ring and from a temperature transition zone located immediately below said ring.

According to another aspect of the invention there is provided a method of forming a container having an integral handle; said method comprising:

- (a) forming a preform having a neck portion and an expandable portion below the neck portion, said neck portion including a locating ring above the expandable portion and a solid stem of orientable thermoplastics material projecting from the preform and moulded integrally therewith, and
- (b) performing a blow moulding operation on said preform to expand the expandable portion to form the body of the container.

Preferably said stem projects from said locating ring and from a temperature transition zone located immediately below said ring.

In a preferred form of the invention, the neck portion and integral handle are subjected to a crystallisation step.

Preferably, the blow moulding operation includes supporting the stem whilst the preform is blown in a manner whereby at least a portion of the external side of the tube expands to encircle at least a lower portion of the stem so as to form an enclosed grip portion between the external side and the solid stem.

10

15

20

25

30

35

It is preferred that the enclosed grip portion allows at least two fingers of the adult human hand to pass therethrough.

In a particularly preferred form of the invention the stem is formed so as to have an I-shaped cross-section at least throughout that portion of the stem where it projects from the external side of said tube. The handle may be curved to provide additional strength.

In a further broad form of the invention there is provided a parison for an injection stretch blow moulding process, said parison formed by an injection process including two separate points of injection.

Preferably a first point of injection permits injection of non-recycled PET or like thermoplastics material. Preferably a second point of injection permits injection of PET or like thermoplastics material incorporating at least a portion of recycled material.

Preferably said first point of injection is for the formation of that part of the parison which will be stretched during a stretch blow moulding operation on the parison. Preferably said second point of injection is for the formation of those parts of said parison which will remain unexpanded or substantially unexpanded in a stretch blow moulding operation on said parison.

In yet a further broad form of the invention there is provided a container manufactured from a two stage injection stretch blow moulding process, said container including a graspable handle affixed at at least a first point and a second point to said container so as to form an enclosed area between the handle and the bottle and through which the fingers of a human hand may be passed.

Preferably said first point of connection comprises an integral connection between the handle and the container and is formed in said first step of said two step operation.

Preferably said second point of connection is formed during said second step of said two step operation.

10

15

20

25

30

Preferably said handle at said second point of interconnection includes a bulbous portion adapted to be at least partially enfolded by a portion of said container as it is blown during said second step of said two step operation whereby a mechanically interlocked connection is formed at said second point of connection of said handle to said container.

In particular preferred forms said bulbous portion comprises one of an upwardly extending hook, a downwardly extending hook, a bulb or a combination of one or more thereof.

In a further broad form of the invention there is provided a method of production of an integral handle PET container including the step of shrouding a handle stem portion of a preform during preheating of said preform preparatory to a stretch blow moulding step.

Preferably the handle stem is fully supported in a mould cavity against movement during the stretch blow moulding operation.

In a further broad form of the invention there is provided a container comprised of biaxially orientable thermoplastic material manufactured from a two stage injection stretch blow moulding process; said two stage process comprising a first stage in which a preform is manufactured and a second stage in which said preform is reheated and biaxially stretched to form said container; said container including a graspable handle affixed at at least a first point of connection and a second point of connection to said container so as to form an enclosed area between said handle and said container and through which at least two fingers of a human hand can pass; and wherein said first point of connection comprises an integral connection between the handle and the container and is formed in said first stage of said two stage process.

BRIEF DESCRIPTION OF THE DRAWINGS

Embodiments of the present invention will now be described by way of example, with reference to the accompanying drawings, in which:

- 5 Fig. 1 is a side view of a prior art parison,
 - Fig. 2 is a side view of a parison incorporating features according to embodiments of the present invention,
 - Fig. 3 is a partial side elevational view of a blow moulded PET container formed from a preform according to one
- 10 embodiment of the invention;
 - Fig. 4 illustrates the steps of formation of a parison according to another embodiment of the invention.
 - Fig. 5A is a side view of a preform according to a further embodiment of the invention;
- Fig. 5B is a side view of a container formed from the preform of Fig. 5A.
 - Fig. 6 is a side view of a die in open position for manufacture of a preform;
 - Fig. 7 is the die of Fig. 6 in closed position;
- Fig. 8 is a side view of the die of Figs. 6 and 7 showing the stem of the preform located therein,
 - Fig. 9 is a top view of a two stage injection, blow mould machine adapted to receive preforms and biaxially orient them into blown containers according to an embodiment of
- 25 the invention,
 - Fig. 10 is a side section view of a lifting, lowering and rotating mechanism for handle covers for use with the machine of Fig. 9,
 - Fig. 11 is an alternative side section view of the mechanism of Fig. 10,
 - Fig. 12 is a side section, close up view of the machine of Fig. 9 showing a preform with handle cover lowered over the handle portion thereof,
- Fig. 13A,B illustrates first and second side section views of a preform adapted for loading into the machine of Fig. 9,
 - Fig. 14 is a perspective view of the preform of Fig. 13,

- Fig. 15 is a perspective view of a container blown from the preform of Fig. 14 on the machine of Fig. 9,
- Fig. 16 is a plan view of a half mould adapted for blowing preforms on the machine of Fig. 9,
- Fig. 17 is a top view of the mould of Fig. 16 with a preform inserted therein ready for blowing on the machine of Fig. 9,
 - Fig. 18 is a bottom view of Fig. 17 with both half moulds in opposed relationship,
- Fig. 19 is a further bottom view of Fig. 17 showing the preform in the position of Fig. 17,
 - Fig. 20 is a section view through the half mould of Fig. 16,
 - Fig. 21 is a section view through the mould of Fig. 16,
- Fig. 22 is a side view of the container of Fig. 15 blown in the mould of Fig. 19 from a preform as illustrated in Fig. 13 and 14,
 - Fig. 23 is a detail, side section view of the neck and top handle portion of the container of Fig. 22,
- Fig. 24 is a side view of a preform incorporating an enlarged first non-expanding region according to a further embodiment of the invention,
 - Fig. 25 is an alternative side view of the preform of Fig. 24,
- Fig. 26 is a side view of a container blown from the preform of Fig. 24 on the machine of Fig. 9,
 - Fig. 27 is a perspective view of the preform of Fig. 24,
 - Fig. 28 is a perspective view of the container of Fig. 26,
 - Fig. 29 is a side view of yet a further alternative
- embodiment of a preform incorporating a lengthened or enlarged first non-expanding zone and adapted for blowing on the machine of Fig. 9,
 - Fig. 30 is a side view of a container blown from the preform of Fig. 29 on the machine of Fig. 9,
- Fig. 31 is a plan view of a half mould for blowing the preform of Fig. 24,

30

35

5

Fig. 32 is a plan view of the half mould of Fig. 31 with the preform of Fig. 24 inserted therein ready for blowing on the machine of Fig. 9,

Fig. 33 is a side section view of a container blown in the mould of Fig. 32 and

Fig. 34 is a detail side section view of the neck and top handle portion of the container of Fig. 33.

Fig. 35 is a first perspective view of a container according to a further embodiment of the invention particularly adapted to resist high internal pressure.

particularly adapted to resist high internal pressures, Fig. 36 is a second perspective view of the container of Fig. 35,

Fig. 37 is a first side view of the container of Fig. 35,

Fig. 38 is a second side view of the container of Fig. 35,

Fig. 39 is a plan view of the container of Fig. 35, Fig. 40 is a side view of a preform from which the

container of Fig. 35 can be blown,
Fig. 41 is a perspective view of the preform of Fig. 40,

Fig. 42 is a perspective view of a container with strap connected handle according to a further embodiment of the invention, and

Fig. 43 is a side view of a preform from which the container of Fig. 42 can be blown.

DETAILED DESCRIPTION OF THE DRAWINGS

A container 10 according to an embodiment of the invention is shown in Fig. 3. It includes a neck 11 and an expanded portion 12.

The neck 11 has a threaded portion 13 and a locating ring 14. Moulded integrally with the ring 14 is a stem 15 having a first portion 15a extending outwardly from the ring 14 and a second portion 15b so inclined to the first portion 15a that it is nearly parallel to a vertical axis of the container 10. In this instance, the first portion 15a subtends an angle of slightly more than 45° to the wall 20 and the second portion subtends an angle of about 20° to the wall 20.

10

15

20

25

30

The particular shape of the stem 15 is selected so that when formed as a handle it may be grasped by fingers of the human hand.

The stem 15 terminates in a stem end 16 which faces generally downwardly in the general direction of closed end of the container 10.

In this instance, the stem 15 is of I-shaped crosssection to combat unwanted effects arising at or near junction 17 of stem 15 with the ring 14 following a blowing operation on the preform 10.

These unwanted effects particularly include stress effects and air inclusions resulting from non-uniform cooling through preform volumes of differing cross-section.

In this embodiment of the invention, the preform is made from PET and is prepared utilizing a heated mould.

In order to produce the container 10, the parison or preform 26 (see Fig. 2) according to an embodiment of the invention can be placed in a blow moulding machine (not shown) and blow moulded according to bi-axial orientation blow moulding techniques with the neck 11 being held in a mould in such a way as not to expand. Initially, the expandable portion of the preform below the neck can be mechanically stretched downwardly to the bottom of the mould and then the bulk of the preform can be blown outwardly by application of compressed air to the extent that a support portion 18 is formed around the stem end 16 such that an enclosed area 19 is formed between wall 20 of the container 10 and the stem 15 in the process of the formation by blow moulding of container 10.

In a particular preferred form of the invention, the enclosed area 19 is of sufficient cross-sectional area to allow at least two fingers of a human hand to be inserted therethrough and to grasp handle 15 so as to support the container 10.

The blow moulding operation is carried out in such a way so as to provide a bottle or container having optimum strength by achieving biaxial orientation of the molecules

35

10

15

20

25

30

35

of the preferred PET material as well as improved barrier properties to reduce oxidation.

In accordance with an embodiment of the invention, the neck 11 and handle 15 can be crystallised by over-heating those parts of the preform. The crystallisation of the handle increases its rigidity which assists orientation of the preform and permits the use of less material.

Crystallisation of the neck and handle can be carried out by running hot oil over the neck and handle, applying an open flame or by blowing hot air.

The location of the handle 15 on the ring 14 ensures that there is minimum interference to the blow moulding process applied to the remainder of the preform. Either a one stage or two stage process can be used.

<u>Detailed Description of Further Embodiments</u>

Fig. 1 illustrates the prior art preform or parison 21 of US 4,629,598. The concept of this prior art disclosure is to form a handle portion 23 from the locating ring of non-expandable portion 22 of the parison 21.

With reference to Fig. 2 and with reference to the detailed description of the preferred embodiment this arrangement of Fig. 1 is modified according to the present invention in a number of respects.

Insets 2A, 2B and 2C show bulbous portions 27 forming part of stem end 16 in the shape, respectively of a downwardly extending hook 24a, a bulb 24b and an upwardly extending hook 24c.

These portions have in common a shape which is adapted to engage mechanically with a blown portion of the container 10 which is adapted to envelop the bulbous portion 27.

The process by which the second stage blow of the expandable portion 12 of parison 26 is effected so as to envelope the bulbous portion 27 of stem end 16 is a stretch blow, biaxial orientation process.

10

15

20

25

30

35

With reference to Fig. 4 a particular method of manufacture of the parison 26 according to another embodiment of the invention is illustrated. It includes a two stage process for the formation of the parison by an injection moulding process. In Stage 1 a first injection mould inlet 28 permits entry of plastics material for the formation of the expanded portion 12 of the parison 26 (expanded in the blow moulding stage of container formation, with reference to Fig. 3).

In a second stage of the injection moulding process for the formation of parison 26 a second injection mould inlet 29 permits entry of plastics material for the formation of the non-expandable portion 25 of parison 26.

The two stage injection arrangement is such that different plastics materials may be injected through first injection mould inlet 28 and second injection mould inlet 29.

In a particular preferred form the plastics material injected in first injection mould inlet 28 is non-recycled or substantially non-recycled plastics material whilst the plastics material injected into second injection mould inlet 29 is recycled or at least partially recycled plastics material.

This arrangement permits controlled use of proportions of recycled and non-recycled plastics material in order to achieve optimum economics in the construction of parison 26.

In a modification of this arrangement the Stage 2 step can include the production of two walls in the non-expandable portion 25 comprising inner wall 51 and outer wall 52. Inner wall 51 is made from virgin or non-contaminated PET material and acts as an insulation barrier with respect to wall 52 which can be made from recycled material 52. This dual wall arrangement can be produced by use of a sliding core arrangement as a modification in the die arrangement and process described with reference to Figs. 6, 7 and 8 later in this specification.

10

15

20

25

30

35

Of course the Stage 1 and Stage 2 steps of Fig. 4 can be interchanged in order.

A parison and resulting container according to a further embodiment of the invention are illustrated in Figs. 5A and B respectively. Like parts are numbered as for previous embodiments.

In this embodiment the parison 21 includes a locating ring 14 immediately below which is a first non-expanding region 30 and a second non-expanding region 31. The first non-expanding region 30 may itself be formed so as to be slightly raised or otherwise differentiated from the expandable portion of parison 21. Second non-expanding region 31 may not be differentiated from the expandable portion of parison 21 but, in use, the blowing operation will be such as to ensure that the second non-expanding region 31 is not expanded in the blowing process.

In this case the stem 15 includes a first rib 32 integrally moulded with and extending from locating ring 14. The stem 15 also includes second rib 33 integrally moulded with and extending from second non-expanding region 31. Stem 15 further includes a rib connector 34 integrally moulded with and extending from first non-expanding region 30 and forming a continuous connection between first rib 32 and second rib 33 throughout the length of stem 15.

The parison 36 of Fig. 5A is then blown in the manner previously described to form the volume 35 of container 37 illustrated in Fig. 5B. The neck portion including stem 15, ring 14, first non-expanding region 30 and second non-expanding region 31 remain unexpanded whilst the expandable portion 36 of parison 36 is biaxially stretched to form the major volume 35 of container 37. The stem end 16 may include the bulbous portions according to the previously described embodiments for connection to container 37 or, either alternatively or in addition can include the application of an adhesive material whereby a chemical bond is formed between stem end 16 and the wall of container 37 by the use of a chemical intermediary.

10

15

20

25

30

35

In a modification of the embodiments of Fig. 5A and Fig. 5B first non-expanding region 30 and second non-expanding region 31 can form part of a single non-expanding region.

In yet a further modification second non-expanding region 31 can be located in the temperature transition zone of the container and wherein minor expansion during the blow moulding step may take place.

In yet a further modification both first non-expanding region 30 and second non-expanding region 31 may be located in the temperature transition zone immediately below the locating ring 14 and, again, minor expansion of these regions may take place during blowing.

With respect to the last two variations described advantage is taken of the observation that expansion at the temperature transition zone can be limited by appropriate mould design and process control whereby unwanted distortion effects caused by the rigid interconnection of this temperature transition zone 30, 31 via second rib 33 and rib connector 34 to ring 14 (or other non-expanding portion of the neck 11) can be controlled.

In use preforms and containers blown therefrom can be manufactured as follows:

A preform is formed from orientable thermoplastics material, preferably PET or like material in an injection moulding process. Slidable dies are illustrated in Figs. 6, 7 and 8 and include a sliding core 40, sliding blocks 41, body 42, base 43, push block 44 and splits holder 45. Fig. 6 illustrates the die in open position, Fig. 7 illustrates the die in closed position and Fig. 8 illustrates a side view showing accommodation of the stem 14.

The completed preforms in a second and preferably separate step are subsequently passed to a stretch blow mould machine where the preforms are first reheated to the appropriate transition temperature (refer introduction). The non-expandable portion of the preform including

10

15

20

25

30

35

locating ring 14 and stem 15 are shielded substantially from the reheat process by appropriate guarding. In most instances there is likely to be a temperature transition zone in the region 30, 31 described with reference to Figs. 5A, 5B.

The reheated preform is then placed in a mould and biaxially stretched and the expandable portion blown to full size utilising processes known in the art. During this process the preform is supported at neck 14 and may also be supported at stem 15. Stem 15 does not take part in the blow process although its stem end 16 may be partially enveloped by an external wall of the blown container.

DETAILED DESCRIPTION OF METHODS OF MANUFACTURE INCORPORATING MODIFIED TWO STAGE STRETCH BLOW MOULDING MACHINES

Fig. 9 illustrates a modified two stage stretch blow mould machine 110 adapted to stretch blow mould (including biaxial orientation) of the preforms of previous embodiments and preforms of further embodiments to be described below with reference to later figures.

The machine 110 comprises a first carousel 111 adapted to receive integral handle preforms 112 from inclined chute 113 into apertures 114 spaced around the periphery thereof.

As first carousel 111 rotates it moves, via apertures 114 the preforms 112 from the chute 113 to a second carousel loading position where the preform 112 is transferred to a spindle 115 mounted near the periphery of second carousel 116.

A sector of approximately 270° of second carousel 116 is arranged as a preheating tunnel 117 where the preforms 112 are progressively heated by a heating bank mounted in opposed relationship to the path of travel of the preforms.

The suitably preheated preforms 112 are loaded consecutively into apertures 119 of a third carousel 120 which acts as a transfer mechanism to both suitably orient the preforms 112 about their longitudinal axis and present

10

15

20

25

30

35

them to a mould cavity 121 comprising first half mould 122 and second half mould 123.

It should be noted that during their time in the preheating tunnel 117 the preforms 112 are rotated about their longitudinal axis by spindles 115 and have a handle shroud 124 mounted over the preform stem which subsequently forms a handle for blown container 125. Details of the rotation of spindles 115 and the shrouding of the preform stem are discussed more fully with reference to Figs. 10, 11 and 12.

Mould cavities 121 are mounted on the periphery of a fourth carousel 126. During their travel through approximately a 270° sector the half moulds 122, 123 rotate to a closed position about their axis 127 and, whilst closed, the preform 112 enclosed therein is blown and biaxially stretched in known manner in order to produce an integral handle, blown container 125. This container 125 is ejected as illustrated when the half moulds open preparatory to receiving a fresh, preheated preform 112.

With reference to Fig. 10 further detail is shown of spindles 115 and handle shrouds 124 and their manner of operation upon and in relation to preforms 112 whilst passing through preheating tunnel 117 on second carousel 116.

The spindles 15 are rotated by band drive 128 so as to, in one embodiment, rotate the preforms 112 through approximately four full axial rotations during their passage through the preheating tunnel 117.

Whilst in the preheating tunnel 117 a handle shroud 124 is lowered over the free end 129 of handle stem 130 so as to fully shroud the handle stem 130 as best seen in greater detail in Fig. 12.

The shroud 124, in one preferred form, is cylindrical save for a fluted open mouth 131 best seen in Fig. 12. The fluted mouth 131 assists in ensuring maximal shrouding of handle stem 130 and also assists in guiding the shroud 124 onto the free end 129 of stem 130.

10

15

20

25

30

35

Lifting and lowering of the shroud 124 is effected through a shroud support stem 132 which is suspended from a cam follower 133 adapted to travel on cam 134.

The stems 132 are themselves rotated by band drive 135 so as to follow the rotation of spindles 115. As best seen in end view of Fig. 11 the shroud support stem 132 is offset from the cam follower stem 136 by virtue of being mounted near the periphery of platten 137.

As cam follower 133 rides up cam 134 it pulls handle shroud 124 up with it by virtue of the connecting link comprising shroud support stem 132, platten 137 and cam follower stem 136.

Cam follower stem 136 can comprise a telescoped arrangement allowing relative axial rotation between two component, telescoping parts thereof.

The handle shroud 124 can comprise alternative shapes other than cylindrical, for example an oval cross section is possible although the cylindrical arrangement having a circular cross section is preferred.

The handle shroud 124 is preferably made of insulating material such as a ceramic material and is covered on an exterior surface 138, in a preferred version, with a heat reflecting material which, ideally, is also light reflecting.

In use the reflective surface 138 causes light and heat emanating from heating bank 118 to be reflected thereof whereby two functions are performed. The first function involves protecting the handle stem 130 from heat. The second function is to reflect heat and light in the direction of that portion of the preform closest to the handle stem 130 so that it is evenly heated and tends not to be shadowed by the stem 130.

In one particular form the handle shrouds 124 can be cooled by an air or nitrogen blast (not shown) directed at them whilst they are lifted clear of the preform 112. This will assist to prevent radiated and/or convected heat building up within the cavity 139 of the shroud 124.

10

15

20

25

30

Figs 13-23 illustrate details of a preform, mould and container blown therefrom and therein by the machine of Fig. 9. With reference to Fig. 13, in a preferred version, dimension A is greater than dimension B thereby to discourage tangling of preforms prior to loading into chute 113.

It will be observed that the top end of the handle is located close to the locating ring in this version. It will also be noted that the stem of the preform which subsequently constitutes the handle of the blown container is fully supported within the half mould during the entire blowing process. In contrast the walls of the container including portions of the container wall peripherally opposite the top end of the handle stem are free to be blown within the constraints of the mould.

With reference to Figs. 24-34 a second version of a preform, mould and resulting blown container is illustrated wherein first non-expanding region 30 is relatively long in the axial direction including a portion 140 which extends from locating ring 141 down to and around at least a top portion of the connection of the handle stem 130 thereby forming a join of the top end of handle stem 130 to locating ring 141. (Best seen in Fig. 24).

In this version there is at least partial expansion of wall portions of the preform located peripherally away from the join of the handle stem 130 to the preform 112 (best seen in Figs 32 and 34). This expansion, relatively, is not as great as the biaxial expansion occurring below the first and second non-expanding regions 30, 31. It can, however, be significant in providing strength and resistance to gas permeation in at least second non-expanding region 31, if not non-expanding region 30.

10

15

20

25

30

35

CONTAINER RESISTANT TO INTERNAL PRESSURES

With reference to Figs. 35 to 39 there is shown a container 150 incorporating an integral handle 151 which is biaxially blown from the preform 152 illustrated in Figs. 40 and 41.

In this instance, as perhaps best seen in Fig. 36, the blown container 150 includes a discontinuity region 153. In this instance the discontinuity region 153 extends the entire circumference of the container 150.

As best seen in Fig. 38 the discontinuity region 153 lies in a plane which subtends an acute angle alpha with a horizontal plane XX.

The plane of the discontinuity region 153 is oriented so that where it passes closest to the integral handle 151 it lies between first end 154 and second end 155 of the handle 151.

In this instance that part of the discontinuity region 153 located furtherest from the handle 151 lies in the plane XX which passes through, or close to, join region 156 where the second end 155 of handle 151 is joined to container 150.

The discontinuity region 153 is formed by a substantial change in direction of the wall of the container 150, perhaps best seen in Fig. 35 wherein first tangent 157 to upper wall portion 158 intersects with second tangent 159 to lower wall portion 160 of container 150 at an obtuse angle beta, thereby forming a portion of the discontinuity region 153.

This discontinuity region 153 imparts additional strength to the container walls, thereby to resist deformation of, particularly from internal pressures which can arise when the container is sealed, as for example when the container contains a carbonated beverage.

In order to assist in the creation of the discontinuity region 153 the preform 152 from which the container 150 is biaxially blown includes different wall thickness profiles, in this instance in the form of first

10

15

20

25

30

35

wall profile 161, second wall profile 162 and third wall profile 163 separated one from the other by first transition zone 164 and second transition zone 165 as best seen in Fig. 40.

It will be observed that the wall thickness of third wall profile 163 is greater than the wall thickness of second wall profile 162 which, in turn, is greater than the wall thickness of first wall profile 161.

The second end 155 of the handle 151 is joined to the container during a biaxial blowing operation by defamation and envelopment about the second end 155. The second end 155 can include a bulbous portion including a bulbous portion of the types illustrated in Fig. 2.

The preform 152 can be manufactured from PET materials in an injection moulding operation as described earlier in this specification.

The preform 152 is then blown as a second stage operation in a stretch blow moulding machine so that its walls conform to the inside surfaces of a mould, also as described earlier in this specification.

TAG CONNECTED HANDLE

With reference to Fig. 42 and Fig. 43 an alternative version of the container and the preform from which it is constructed are illustrated.

With reference to Fig. 42 the container 201 includes an integral handle 202 as previously described and constructed, save that the connection to the lower end of the container 201 is formed as an integral connection by way of a tag 203 which extends from a lower edge 204 of a wide part of the handle 202 down to a mid circumferential portion 205 of container 201 at which point it is integrally connected thereto. The lower edge 204 of the wide part of the handle 202 includes a landing portion 206 which merely rests on the surface of the container 201 at this point rather than being integrally connected thereto or otherwise connected thereto at this point.

10

15

A preform 207 from which the container 201 of Fig. 42 is blown is illustrated in Fig. 43. This preform 207 is constructed substantially in the same manner as that illustrated in Fig. 40 except that lower edge 204 of handle 202 is integrally connected to the preform 207 by way of tag 203 in the manner illustrated in Fig. 43.

The preform 207 is blown to form the container of Fig. 42 utilising the process previously described with reference to Figs. 10, 11 and 12.

The above describes only some embodiments of the present invention and modifications obvious to those skilled in the art can be made thereto without departing from the scope and spirit of the present invention.

INDUSTRIAL APPLICABILITY

Embodiments of the invention are applicable to the manufacture of containers made from orientable thermoplastics material and incorporating a handle or like grasping fixture as an integral component of the container.

CLAIMS

- 1. A preform for a container comprised of orientable thermoplastic material and arranged so that the resultant blown container will include a handle or like support structure; said preform comprising a moulded structure having a neck portion and an expandable portion below the neck, said neck including a locating ring above the expandable portion and a solid stem of orientable thermoplastics material projecting from the preform and moulded integrally therewith which when the container is formed constitutes the handle.
- 2. A method of forming a container having an integral handle; said method comprising:
 - (a) forming a preform having a neck portion and an expandable portion below the neck portion, said neck portion including a locating ring above the expandable portion and a solid stem of orientable thermoplastics material projecting from the preform and moulded integrally therewith, and
 - (b) performing a blow moulding operation on said preform to expand the expandable portion to form the body of the container.
- 3. The method of claim 2 wherein the neck portion and integral handle are subjected to a crystallisation step.
- 4. The method of claim 2 wherein the blow moulding operation includes supporting the stem whilst the preform is blown in a manner whereby at least a portion of the external side of the tube expands to encircle at least a lower portion of the stem so as to form an enclosed grip portion between the external side and the solid stem.
- 5. The method of claim 4 wherein the enclosed grip portion allows at least two fingers of the adult human hand to pass therethrough.

- 6. The method of claim 2 wherein the stem is formed so as to have an I-shaped cross-section at least throughout that portion of the stem where it projects from the external side of said tube.
- 7. A parison for an injection stretch blow moulding process, said parison formed by an injection process including two separate points of injection.
- 8. The parison of claim 7 wherein a first point of injection permits injection of non-recycled PET or like thermoplastics material.
- 9. The parison of claim 7 or 8 wherein a second point of injection permits injection of PET or like thermoplastics material incorporating at least a portion of recycled material.
- 10. The parison of claim 7 or 8 wherein said first point of injection is for the formation of that part of the parison which will be stretched during a stretch blow moulding operation on the parison.
- 11. The parison of claim 9 wherein said second point of injection is for the formation of those parts of said parison which will remain unexpanded or substantially unexpanded in a stretch blow moulding operation on said parison.
- 12. A container manufactured from a two stage injection stretch blow moulding process, said container including a graspable handle affixed at at least a first point and a second point to said container so as to form an enclosed area between the handle and the bottle and through which the fingers of a human hand may be passed.
- 13. The container of claim 12 wherein said first point of connection comprises an integral connection between the handle and the container and is formed in said first step of said two step operation.
- 14. The container of claim 13 wherein said second point of connection is formed during said second step of said two step operation.

- 15. The container of claim 14 wherein said handle at said second point of interconnection includes a bulbous portion adapted to be at least partially enfolded by a portion of said container as it is blown during said second step of said two step operation whereby a mechanically interlocked connection is formed at said second point of connection of said handle to said container.
- 16. The container of claim 15 wherein said bulbous portion comprises one of an upwardly extending hook, a downwardly extending hook, a bulb or a combination of one or more thereof.
- 17. The container of any one of claims 12 to 16 wherein an adhesive is utilised to assist connection at said second point of interconnection.
- 18. The preform of Claim 1 further including a locating ring immediately below which is a first non-expanding region and a second non-expanding region.
- 19. The preform of Claim 18 wherein the first nonexpanding region is formed so as to be slightly raised or otherwise differentiated from the expandable portion of parison.
- 20. The preform of Claim 18 or 19 wherein the second nonexpanding region is not differentiated from the expandable portion of parison.
- 21. The preform of any one of Claims 18-20 wherein the stem includes a first rib integrally moulded with and extending from locating ring.
- 22. The preform of Claim 21 which also includes a second rib integrally moulded with and extending from said second non-expanding region.
- 23. The preform of Claim 22 which further includes a rib connector integrally moulded with and extending from first non-expanding region and forming a continuous connection between said first rib and said second rib throughout the length of said stem.

- 24. The preform of any one of Claims 18-23 and wherein said second non-expanding region forms part of a temperature transition zone.
- 25. The preform of any one of Claims 18-24 and wherein said first non-expanding region forms part of said temperature transition zone.
- 26. The preform of Claim 24 or Claim 25 wherein deformation of said temperature transition zone takes place during a stretch blow moulding process.
- 27. The preform of any one of Claims 18-26 manufactured by a two stage injection moulding process wherein material is injected at different locations in the die to form a preform adapted to be composed from more than one type of material.
- 28. The preform of Claim 27 wherein during at least one stage of said two stage process an inner wall and outer wall of said preform is formed, said inner wall adapted to be made from a different material from said outer wall.
- 29. A container stretch blow moulded from the preform of any one of claims 18-28.
- 30. A container made from PET material and stretch blow moulded from the preform of any one of Claims 18-29.
- 31. A container comprised of biaxially orientable thermoplastic material manufactured from a two stage injection stretch blow moulding process, said container including a graspable handle affixed at at least a first point and a second point to said container so as to form an enclosed area between the handle and the bottle and through which the fingers of a human hand may be passed.
- 32. The container of claim 31 wherein said first point comprises an integral connection between the handle and the container and is formed in said first step of said two step operation.
- 33. The container of claim 31 or claim 32 wherein said second point of connection is formed during said second step of said two step operation.

- 34. The container of claim 33 wherein said handle at said second point of interconnection includes a bulbous portion adapted to be at least partially enfolded by a portion of said container as it is blown during said second step of said two step operation whereby a mechanically interlocked connection is formed at said second point of connection of said handle to said container.
- 35. The container of claim 34 wherein said bulbous portion comprises one of an upwardly extending hook, a downwardly extending hook, a bulb or a combination of one or more thereof.
- 36. The container of any one of claims 31 to 35 wherein an adhesive is utilised to assist connection at said second point of interconnection.
- 37. The container of any one of claims 31 to 36 further including a locating ring at a neck portion thereof immediately below which is a first non-expanding region.
- 38. The container of claim 37 further including a second non-expanding region below said locating ring.
- 39. The container of Claim 37 or Claim 38 wherein the first non-expanding region is formed so as to be slightly raised or otherwise differentiated from the expandable portion of parison.
- 40. The container of Claim 37 or Claim 38 wherein the second non-expanding region is not differentiated from the expandable portion of parison.
- 41. The container of any one of Claims 31-40 wherein said handle includes a first rib integrally moulded with and extending from said locating ring.
- 42. The container of Claim 41 wherein said handle includes a second rib integrally moulded with and extending from said second non-expanding region.
- 43. The container of Claim 41 or Claim 42 which further includes a rib connector integrally moulded with and extending from said first non-expanding region and forming a continuous connection between said first rib

- and said second rib throughout the length of said handle.
- 44. The container of any one of Claims 31-43 and wherein said second non-expanding region forms part of a temperature transition zone.
- 45. The container of any one of Claims 31-44 and wherein said first non-expanding region forms part of said temperature transition zone.
- 46. The container of any one of Claims 31-45 wherein deformation of said temperature transition zone takes place during a stretch blow moulding process.
- 47. The container of any one of Claims 31-46 manufactured by a two stage injection moulding process wherein material is injected at different locations whereby said container is composed from more than one type of material.
- 48. The container of Claim 47 wherein during at least one stage of said two stage process an inner wall and outer wall of said preform is formed, said inner wall adapted to be made from a different material from said outer wall.
- 49. A method of production of an integral handle PET container including the step of shrouding a handle stem portion of a preform during preheating of said preform preparatory to a stretch blow moulding step.
- 50. The method of Claim 49 wherein the handle stem is fully supported in a mould cavity against movement during the stretch blow moulding operation.
- 51. A container comprised of biaxially orientable thermoplastic material manufactured from a two stage injection stretch blow moulding process; said two stage process comprising a first stage in which a preform is manufactured and a second stage in which said preform is reheated and biaxially stretched to form said container; said container including a graspable handle affixed at at least a first point of connection and a second point of connection to said container so as to form an enclosed area between said handle and said container and through which at least

- two fingers of a human hand can pass; and wherein said first point of connection comprises an integral connection between the handle and the container and is formed in said first stage of said two stage process.
- 52. The container of claim 51 wherein said second point of connection is formed during said second stage of said two stage process.
- 53. The container of claim 52 further including a locating ring at a neck portion thereof.
- 54. The container of claim 53 wherein said handle at said second point of connection includes a bulbous portion which is at least partially enfolded by a portion of said container as it is blown during said second stage of said two stage process whereby a mechanically interlocked connection is formed at said second point of connection of said handle to said container.
- 55. The container of claim 54 wherein said bulbous portion comprises one of an upwardly extending hook, a downwardly extending hook, a bulb or a combination of one or more thereof.
- 56. The container of claim 55 wherein an adhesive is utilised to assist connection at said second point of connection.
- 57. The container of claim 54 further including a first non-expanding region immediately below said locating ring.
- 58. The container of claim 57 further including a second non-expanding region below said first non-expanding region.
- 59. The container of claim 57 wherein said first nonexpanding region is formed so as to be slightly raised or otherwise differentiated from that portion of said container which is fully biaxially oriented during said second stage of said two stage process.
- 60. The container of claim 58 wherein said second nonexpanding region is not differentiated from that portion of said container which is fully biaxially oriented during said second stage of said two stage process.

- 61. The container of claim 58 or claim 59 wherein minor expansion of said second non-expanding region takes place during said second stage of said two stage process.
- 62. The container of claim 58 wherein said handle includes a first rib integrally moulded with and extending from said locating ring.
- 63. The container of claim 62 wherein said handle includes a second rib integrally moulded with and extending from said second non-expanding region.
- 64. The container of claim 63 which further includes a rib connector integrally moulded with and extending from said first non-expanding region and forming a continuous connection between said first rib and said second rib throughout the length of said handle.
- 65. The container of claim 58 wherein said second nonexpanding region forms part of a temperature transition zone.
- 66. The container of claim 57 wherein said first nonexpanding region forms part of a temperature transition zone.
- 67. The container of claim 66 wherein deformation of said temperature transition zone takes place during a stretch blow moulding process.
- 68. The container of claim 51 manufactured by said two stage injection moulding process and wherein material is injected at different locations during formation of said preform during said first stage of said two stage process whereby said container can be composed from more than one type of material.
- 69. The container of claim 68 wherein during said first stage of said two stage process an inner wall and outer wall of said preform is formed, said inner wall made from a different material from said outer wall.
- 70. The container of any one of claims 51-69 further including a discontinuity region as defined in the specification.
- 71. The container of Claim 70 wherein said discontinuity region lies in a plane which lies at an acute angle to AMENDED SHEET (Article 34) (IPEA/AU)

- the horizontal, said discontinuity region extending substantially throughout the circumference of said container.
- 72. The container of any one of Claim 70 or Claim 71 wherein said discontinuity region at its point closest to said handle is located between a first end and a second end of said handle.
- 73. A preform from which the container of any one of Claims 51 to 72, said preform including more than one wall profile.
- 74. The preform of Claim 73 wherein said preform has a first wall profile closest to its neck followed by a second wall profile immediately there below and separated therefrom by a first transition zone.
- 75. The preform of Claim 74 wherein said preform further includes a third wall profile immediately below said second wall profile and separated therefrom by a second transition zone.
- 76. The container of any one of claims 31 to 38 wherein said graspable handle is affixed at said second point by way of a tag.
- 77. The container of claim 76 wherein said tag extends from a lower edge of a wide portion of said handle and is integrally connected at a mid circumferential portion of said container.
- 78. The container of claim 76 or 77 wherein said lower edge of said wide portion of said handle includes a landing portion which rests on but is not otherwise connected to or enveloped by an outer surface of said container.
- 79. A preform from which the container of any one of claims 76 to 78 is blown, said preform including a tag extending from a lower edge of a handle portion of said preform; said tag being integrally connected to said preform.




Fig. 1 Prior Art




Fig. 2





Fig. 3






Fig. 5B




Fig. 6

PCT/AU98/00738 Received 09 April 1999

7/31




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12







Fig. 13

14/31





15/31






Fig. 18




Fig. 19






Fig. 20






Fig. 21





Tig. 2




Fig. 24




Fig. 25




Fig. 26




Fig. 27




Fig. 28




Fig. 29







Fig. 30

23/31



24/31





25/31




Fig. 35





Fig. 36



150 150 150 150 150 Fig. 37 Fig. 38




Fig. 40




Fig. 41






Fig. 42




Fig. 43

Please tyl	Under th) inside this bax === na Paperwork Redu SARS control number	ction Act o	it 1995, no	persons &	Patent and ' ne required t	T-make and a state of	CORPORE HIS F	YPAR	PTO/S8/01 /30/00. OMB 069 TMENT OF COM rmation unloss it	51-0032 " MERCE
D		RATION		tility	or C)esig	n Pa	tent A	pp	lication	
United St	lates of America lates or PCT into	under 35 U.S.G. 12 I, listed below and, imutional application real to pasentability nternational filing da	es ustones en set ni n enfenises es	anner provi d in 37 CF	ided by the		enh of 35 i	15C 112 L	cionav	ledine the duty to	disclose
		nt Application Number			·	Parent F (MM/D	iling Da			nt Palent Nur (If applicable)	
1 400	Bonal U.S. of PC	T international app	lication nu	imbers are	feted on a	supplemen	tal priority	data sheet PT	CVSEVO	72B attached her	ito
As a nam	ed streeter, I he	reby appoint the fol	lowing reg	istered pra	cotioner(s)	to prosecu	o this appli	ication and to	-	at all business in t	he Pasent
and Trade	erturk Office con	vnected therewith:	Cueto	mer Numb	007	553	J·		-	Place Custom Number Bay Co	
						amo/registr	ation numb	er listed below	<u>. </u>	Label here Registre	المسلم
	Herne	1		Registr Num				Name		Numb	
	M. STETIN			9,445				BRUNDA		28,497	
	B. GARRE			4,823				J. BKUC		35,462	
	HEW A. NE LL ANDERS			6,224 0,990			-	. NABER TANEZAK		26,777 40,196	
		practitioner(s) nam	<u> </u>		Registered						
		nce to: 🔽 Cus		umber	00766	-	7			ondence addres	
Name	Lox	vell Anders	on								
Addre	STE	TINA BRUND	A GAR	REO &	BRUCK	ER					
Addre	242	'21 Calle d	e la l	Louisa	, 4th	Floor					
City	Lag	una Hilis				State	CA	ZIP	92	?65 <i>3</i>	····
Count	ry ÚSA	į.		Telephon	e (94	9) 855	-1245	Fax	(949	9) 855-637	1
punisha	i to be true; and ble by fine or to	statements made further that these sprisorment, or bot accused thereon.	****	Ne water m	ada with t	NA HIDOMARK	na shat will	ra trice scate	27/10/01	200 THE RES TO 1	MAKE BOSE
Name	of Sale or F	irst inventor:				☐ A pet	tion has t	seen filed fo	r th is t	unsigned invent	101
بإب	Given Nan	ne (first and mide	le fit any	D			F	amily Name	oc Su	тате	
1-134	enn Robe	ert_	1	/		3	eale				
Invent Signal		X M	ear	<u>, </u>						Dets/6	1/200
Reside	mor: City	Kings Lan	gley	Stato	AU	Count	y Aus	tralia		Cilizenship	ر ٠
Post 0	ffice Address	9 Conway	Place								
Post C	office Address										

NOV 0 6 2000 B

NSW 2147

Australia

Country

supplemental Additional Invertor(s) sheet(s) PTO/SB/02A attached hereto

Kings Langle

Additional inventors are being named on the

NOV 0 6 2000

Please type to plus sign (+) thekte this box> Under the Paperwork Reduction Act of 1995, no persons a self-to OMB control number.	Total Indiana Carre 110	PTO/98/01 (12-97) hrough 9/30/00. OMD 0651-0032 DEPARTMENT OF COMMERCE n of information unless it contains		
	Attorney Docket Number	WOUMR-0016S BEALE, Glenn Robert		
DECLARATION FOR UTILITY OR DESIGN	First Named Inventor			
PATENT APPLICATION	COMPLETE IF KNOWN			
(37 CFR 1.63)	Application Number	09 / 508,353		
_unsigned	Filing Date	Mar. 09, 2000		
Declaration Submitted OR Submitted after Initial	Group Art Unit	Unknown		
with Initial Filing (surcharge (37 CFR 1.16 (e)) required)	Examiner Name	Unknowa		

with Initial Filing	Filing (surcharge (37 CFR 1.16 (e)) required)	Examiner Name	Ur	iknowa	
s national am the original fl	ddress, and citizenship are at	one name is fisted below?	or an original, firs	st and joint inver	itor (if plura)
	H INTEGRAL HANDI MANUFACTURE				
the specification of which	(Title	of the Invention)			
is attached hereto OR					
was fled on (MM/D0	m 39/09/199	as United	States Appacat	on Number or P	ÇT international
polication Number PCT/	AU98/00738 and was	Amended on (MMDDY)	m		(if applicable).
neraby claim foreign priorit rulicate, or 385(s) of any	ectose information which is no y benefits under 35 U.S.C., P.C.T international application we also identified below, by di polication having a filing date	118(a)-(d) or 365(b) of ar which designated at isa	y foreign applica at one country o	ation(s) for pate ther than the U	
rior Foreign Application Number(s)	Country	Foreign Fifing Data (MM/DD/YYYY)	Priority Not Claimed	Certified Co	py Attached?
PO 9080 PP 0982 PP 3441	Australia Australia Australia	09/09/1997 12/17/1997 05/03/1998	0000	معمه	日路路田
Additional foreign applic	ation numbers are listed on a	supplemental priority deta	sheet PTO/SE/C	28 attached he	reto:
I hereby claim the benefit a Application Number	ander 35 U.S.C. 119(e) of an	Chited States provisions	#DONCE VOIN(S) 14	ARG DROW.	^
Аррисации потом	(e) Famig Dati	s (mag Down 1 1 1 s)	dmun	onal provision ers are listed o emental priorit SB/028 attach	on a y data sheet

[Page 1 of 2]

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case, Any comments on the emount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. OO NOT SEND FEES OR COMPLETED PORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Parents, Washington, DC 20231.

Please type a plus sign (+) triside this box -> +

PTO/S8/02C (3-97)

Approved for use through 9/30/98. ONS 06S1-0032

Parent and Trademark Officer U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it confidence is used OMS control number.

DECLARATION

REGISTERED PRACTITIONER INFORMATION (Supplemental Sheet)

Name	Registration Number	Name	Registration Number
ERIC K. PROUL	45,025		
	·		
Hard Bard and Bard the first world been their burd that their than the conditions of			
<u>=</u> .			
70 10 10 10 10 10 10 10 10 10 10 10 10 10			
•			

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case, Any consents on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Tradement Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.